

SCHEDA TECNICA – DATA SHEET

DESCRIZIONE PRODOTTO – PRODUCT DESCRIPTION

- **Codice articolo Iperceramica** – Item code Iperceramica: **PE BASIC**
- **Colore** - Color: Nero - Black
- **Descrizione** – Description: Rotolo in polietilene espanso con densità standard e spessore 2 mm. Roll of standard density polyethylene foam with a thickness of 2 mm



DIMENSIONI PRODOTTO – PRODUCT DIMENSIONS

Proprietà Properties	Metodo di prova Test Method	Unità Unit	Valore Value	Tolleranze Tolerances	
				Min	Max
Spessore Thickness	ISO 1923	[mm]	2	-10%	+10%
Densità nominale Density	ISO 845	[kg/m³]	15,5	-10%	+10%
Massa superficiale Area weight	Interno Internal	[g/m²]	31	-10%	+10%
Altezza Width	ISO 1923	[mm]	1000	0	+30
Lunghezza Length	ISO 1923	[m]	20	-3%	+3%

DATI TECNICI – TECHNICAL DATA

Stress alla compressione (CV%) Compression Stress	ISO 3386-1	[kPa]	25%: 11	
			50%: 54	
			70%: 141	
Resistenza alla compressione (CS: 0.5mm - 25%) Compressive strength	EN 826 + A.3.7	[kPa]	CS0	≤ 10
Resistenza al carico dinamico Dynamic load resistance	EN 13793	[Cicli] [Cycles]	≤ 10000	

The data and information represented above are intended as general guide only and are not construed as specification limits. All the above information is given in good faith and in accordance with our knowledge and experience.

Isolamento al calpestio Impact sound insulation	EN 10140-3	[dB]	16
Rumore da calpestio Walking noise on floors	EN 16205	[SONE]	≥ 110
Resistenza termica Thermal resistance	EN 12667	[m²K/W]	0,044
Stabilità termica (24H) Thermal stability	EN 1604	[°C]	70
Resistenza alla fiamma Reaction to fire	EN 13501	[Classe] [Class]	Efl
Emissione composti organici volatili (VOCs) Emission of volatile organic compounds (VOCs)	ISO 16000-9	[Classe] [Class]	A+
Resistenza alla diffusione del vapore acqueo (SD) Water vapour diffusion resistance	EN 12086	[m]	Attenuata

CARATTERISTICHE QUALITATIVE – QUALITATIVE CHARACTERISTICS

- **Difetti visivi:** pieghe, aspetto della cella, residui di colla, bolle, forature, bruciature e altre impurità sono ammesse su superfici inferiori al 2% della lunghezza totale.
- **Allineamento dei bordi laterali:** ammessa una fluttuazione massima di 60 mm per lato
- **Sezionati:** minima altezza 100 mm, tolleranza -10/+30 mm.
- **Alignment of the lateral side:** max 60 mm on each side.
- **Visible defects:** folds, appearance of the cell, glue residues, blisters, punctures, burns and other impurities are permitted on surfaces less than 2% of the total length.
- **Cut Reels:** minimum width 100 mm, tolerance -10/+30 mm.

The data and information represented above are intended as general guide only and are not construed as specification limits. All the above information is given in good faith and in accordance with our knowledge and experience.